

## CLT - 234

**DESCRIPTION:** This product is designed to provide scale and corrosion protection for closed chilled-loop, hot water and steam systems. It provides excellent corrosion protection even at elevated temperatures by establishing a protective film within the system. When used in steam boiler applications, this product should be used in conjunction with SBT - 445 in order to provide corrosion protection for the entire system including steam lines.

**DIRECTIONS:** For maximum corrosion protection, a sodium molybdate level of 150-200 ppm (50-80 ppm molybdenum) should be maintained within the system by using a feed rate of approximately 1:600. The pH of the boiler blow down should be kept in the range of 8.0 - 8.5.

In a new steam system, the initial feed rate should be increased to 1:200 for a period of 1 - 2 weeks to establish a protective film and then reduced to the normal feed rate of 1:600.

FOR COMMERCIAL USE

